

TUNGSTEN

By Kim B. Shedd

Domestic survey data and tables were prepared by Eric A. Seavey, statistical assistant, and the world production table was prepared by Glenn J. Wallace, international data coordinator.

Tungsten has a wide range of industrial uses, the largest of which is as tungsten carbide in cemented carbides. Cemented carbides (also called hardmetals) are wear-resistant materials used by the metalworking, mining, and construction industries. Tungsten metal wires, electrodes, and/or contacts are used in lighting, electronic, electrical, heating, and welding applications. Tungsten is also used to make heavy metal alloys for armaments, heat sinks, and high-density applications, such as weights and counterweights; superalloys for turbine blades; tool steels; and wear-resistant alloy parts and coatings. Chemical uses of tungsten include catalysts, inorganic pigments, and high-temperature lubricants.

U.S. tungsten mines remained closed in 1999. China continued to be the largest supplier of tungsten imports to the United States. Russia was also a significant supplier. In 1999, 66% of all tungsten imports to the United States was from these two countries.

In June, the Defense National Stockpile Center (DNSC), U.S. Department of Defense (DOD), began selling tungsten materials from the National Defense Stockpile (NDS). The last releases of tungsten from the NDS were during the ferroalloy upgrading program, which was completed in 1989. Tungsten ores and concentrates were released as payment during and in support of that program.

The important U.S. and world tungsten statistics for 1999 and the previous 4 years are listed in table 1. Most data in this report have been rounded to three significant digits. Totals and percentages were calculated from unrounded numbers. Unless otherwise specified, all statistics in this report are in metric tons of contained tungsten.

Tungsten prices and many tungsten statistics from other sources are quoted in units of tungsten trioxide (WO_3). The short ton unit, which is used in the United States, is 1% of a short ton (20 pounds), and WO_3 is 79.3% tungsten. A short ton unit of WO_3 , therefore, equals 20 pounds of WO_3 and contains 7.19 kilograms (kg) (15.86 pounds) of tungsten. The metric ton unit, which is used in most other countries, is 1% of a metric ton (10 kg). A metric ton unit of WO_3 , therefore, equals 10 kg of WO_3 and contains 7.93 kg (17.48 pounds) of tungsten.

Legislation and Government Programs

In August, the International Trade Administration, U.S. Department of Commerce, and the U.S. International Trade Commission announced that they were each conducting a review of the antidumping duty order on U.S. imports of tungsten ore concentrates from China. The reviews were intended to determine whether revoking the antidumping duty

would be likely to lead to a continuation or recurrence of dumping or material injury to the domestic industry. As a result of the reviews, the 151% duty on imports of tungsten ore concentrates from China was revoked effective January 1, 2000 (International Trade Administration, 1999a, b; U.S. International Trade Commission, 1999a, b).

In late June, the DNSC began selling tungsten materials. Five negotiated sales were held during calendar year 1999—three for tungsten ores and concentrates and two for ferrotungsten, tungsten carbide powder, and tungsten metal powder. As shown in table 2, 1,890 metric tons (t) of tungsten contained in ores and concentrates, ferrotungsten, tungsten metal powder, and tungsten carbide powder was sold during the calendar year. During fiscal year 1999 (October 1, 1998, through September 30, 1999), 1,590 t of contained tungsten was sold; this represented 79% of the maximum amount available for sale in the Annual Materials Plan (AMP). Of the tungsten sold, however, 98% had not been shipped by the end of the fiscal year (U.S. Department of Defense, 2000, p. 16, 44). The AMP for fiscal year 2000 (October 1, 1999, through September 30, 2000) set the maximum quantities of tungsten materials that could be sold, in metric tons of contained tungsten, as follows: tungsten ores and concentrates, 1,810; tungsten carbide powder, 454; ferrotungsten, 136; and tungsten metal powder, 68 (Defense National Stockpile Center, 2000). The quantities of tungsten materials remaining in the stockpile at yearend, including those committed for sale and pending shipment, are listed in tables 1 and 2.

The U.S. Fish and Wildlife Service (FWS) granted final approval of two tungsten-based shot products for hunting waterfowl and coots—tungsten-iron shot and tungsten-polymer shot. In addition, the FWS granted temporary approval of tungsten-matrix shot for hunting waterfowl and coots during the 1999-2000 hunting season (U.S. Fish and Wildlife Service, 1999).

As part of a DOD initiative to eliminate the use of hazardous materials in the production of small caliber ammunition, the U.S. Army Armament Research, Development and Engineering Center at Picatinny Arsenal, NJ, established a joint working group comprised of various DOD entities and three U.S. Department of Energy laboratories in 1995. One component of the “Green Bullet” program was to find an alternative for the lead-antimony cores in small-caliber ammunition projectiles. Seven composite materials, each of which contained tungsten as the high-density component, were evaluated for ease of production and ballistics performance. Tungsten-nylon and tungsten-tin composites were identified as potential substitutes for lead-antimony in the cores of 5.56-millimeter (mm)

projectiles. Continued efforts during 1999 included finalizing the 5.56-mm projectile configuration and qualifying the new bullet as an alternate for the M855 service round (U.S. Army Armament Research, Development and Engineering Center, March 31, 1999, Green ammunition projects—Projectile core replacement, accessed March 30, 2000, at URL <http://www.pica.army.mil/greenammo/projects.htm>; U.S. Army Environmental Center, January 14, 2000, Green small caliber ammunition, accessed April 12, 2000, at URL <http://aec.army.mil/prod/usaec/et/xxi/nontox.htm>). Samples of the lead-free ammunition were tested by the Alaska Army National Guard and the Massachusetts National Guard. In December, the first production lot of tungsten-based bullets was manufactured at the Lake City Army Ammunition Plant near Independence, MO (U.S. Army Materiel Command, December 1999, Green bullet first production lot manufactured, AMC Technology Snapshots, accessed April 12, 2000, via URL <http://www.pica.army.mil/greenammo/press/pressindex.htm>; Bill Vagt, Alaska Army National Guard, January 14, 2000, Guard unit tests “green” ammo—Alaska soldiers fire lead-free service rounds on range, Environmental Update, v. 11, no. 1, accessed April 12, 2000, at URL <http://aec.army.mil/prod/usaec/op/update/win99/w9901.htm>).

Production

Domestic production statistics for tungsten are based on data collected by the U.S. Geological Survey (USGS) by means of two separate voluntary surveys. Statistics that result from these surveys are listed in tables 1 and 3.

The annual Tungsten Ore and Concentrate Survey covered the production, purchases, disposition, and stocks of tungsten ores and concentrates. No tungsten was mined in the United States in 1999. The Pine Creek Mine in Bishop, CA, which was owned equally by Avocet Mining PLC (Avocet) and Strategic Minerals Corp., remained under care and maintenance.

The monthly Tungsten Concentrate and Tungsten Products Survey canvassed companies that produced tungsten carbide powder, tungsten chemicals, and/or tungsten metal powder from ammonium paratungstate, tungsten-bearing scrap, and tungsten concentrate. The USGS received responses from 12 of the 13 processing operations on the survey; estimates were made for the nonresponding operation.

Major U.S. processors of tungsten materials in 1999 included Avocet Tungsten Inc., Bishop, CA; Buffalo Tungsten Inc., Depew, NY; General Electric Co., Euclid, OH; Kennametal Inc., Latrobe, PA, and Fallon, NV; OM Group, Inc., Midland, MI, and St. George, UT; Osram Sylvania, Inc., Towanda, PA; and Teledyne Metalworking Products, Huntsville, AL.

In 1999, U.S. processors consumed 18% less tungsten concentrate but significantly more tungsten-bearing scrap than in 1998. Domestic production of ammonium paratungstate was higher than that of 1998 but remained less than that of 1997. Reported consumption of ammonium paratungstate was 26% less in 1999 compared with that of 1998. Total net production of all primary tungsten products (hydrogen-reduced metal powder, tungsten carbide powder, and tungsten chemicals)

decreased by 16% in 1999 compared with that of 1998.

Avocet Tungsten produced ammonium paratungstate and ammonium metatungstate from ore concentrates and tungsten-bearing scrap at its tungsten-processing plant in Bishop. Early in the year, North American Tungsten Corp. Ltd. of Vancouver, British Columbia, sold its interest in the ammonium metatungstate (AMT) equipment at the Bishop plant. The equipment had been leased to Avocet in return for a 50% interest in the operating profits from the AMT (North American Tungsten Corp. Ltd., 1998, 1999). The narrowing differential in prices for the Bishop plant’s products, particularly ammonium paratungstate, in relation to the price of its feedstocks caused Avocet to question the continued economic viability of the plant. The company reduced the number of employees working at the plant, decreased production levels, and drew down feedstock inventories. In spite of a reduction in operating losses, Avocet was considering various options for the future of the plant; these options included forming a strategic partnership, selling the plant, or closing it. No decision on the plant’s future had been made by yearend (Avocet Mining PLC, September 29, 1999, Chairman’s statement—Tungsten, Annual Report and Accounts 1999, accessed June 26, 2000, at URL <http://www.avocet.co.uk/accounts/1999AR/chairman.htm>).

Startup of Nanodyne Inc.’s nanocrystalline powder plant in Laurinburg, NC, was delayed by technical problems. The plant will have the capacity to produce 500 metric tons per year (t/yr) of composite metal powders by using the company’s proprietary spray-conversion process. In addition to tungsten carbide-cobalt powders, Nanodyne was also developing tungsten-silver and tungsten-copper powders to be used as electrical contacts by the semiconductor industry. Nanodyne was a wholly owned subsidiary of N.V. Union Minière S.A. of Brussels, Belgium. The Nanodyne plant is adjacent to Union Minière’s Carolmet Cobalt Products plant, which produced cobalt metal powder and salts (American Metal Market, 1998; N.V. Union Minière S.A., 2000, p. 26).

Consumption

Statistics on consumption of tungsten in end-use categories by U.S. metal consumers were developed from the voluntary Consolidated Consumers Survey. For this survey, nearly 75 tungsten consumers were canvassed on a monthly or annual basis. Reported consumption and stocks data in tables 1 and 4 include estimates to account for nonrespondents. Total U.S. reported consumption of tungsten materials to make alloys, catalysts, cemented carbides, mill products, and pigments decreased by 8% in 1999 compared with that of 1998. In 1999, U.S. industry consumed less ferrotungsten, tungsten carbide powder, tungsten chemicals, and tungsten scrap but more tungsten metal powder than in 1998. Producers of cemented carbides, pigments, steels, superalloys, and other alloys reported decreased tungsten consumption in 1999, and producers of catalysts and mill products for lighting and other industries reported increased tungsten consumption.

Weekly reports of the number of operating drilling rigs give an indication of the demand for cemented carbide components

by the oil drilling industry. The number of rigs that operated in the United States decreased from 600 in early January to a low of 488 on April 23. This was the lowest U.S. rig count since recording began in 1940. During the remainder of the year, the number of operating rigs increased to a high of 815 in mid-December. During 1999, the average number of operating rigs in the United States was 625, which was 26% lower than the 843 operating rigs in 1998 (Baker Hughes Inc., 2000, North American rig counts, accessed April 3, 2000, at URL http://www.bakerhughes.com/investor/rig/rig_na.htm).

In 1999, total consumption of tungsten scrap by U.S. processors and consumers was 5,250 t of contained tungsten, which was a 57% increase from the 3,350 t consumed in 1998.

Prices

Prices of tungsten materials, as published in Metal Bulletin and Platt's Metals Week, remained at relatively low levels in 1999, in spite of increases during the second half of the year. Monthly and annual average prices of tungsten concentrates are listed in table 5. The average of tungsten concentrate prices reported by Metal Bulletin in 1999 was \$40 per metric ton unit, which was 9% lower than that of 1998. The average of U.S. spot tungsten ore concentrate prices reported by Platt's Metals Week in 1999 was \$47 per metric ton unit (\$43 per short ton unit), which was 10% lower than that of 1998.

Ammonium paratungstate prices were also lower than those of 1998. The average of high and low prices of ammonium paratungstate in the U.S. market reported by Platt's Metals Week remained stable at \$57 per metric ton unit (\$52 per short ton unit) throughout the year. The average of high and low prices of ammonium paratungstate in the U.S. market reported by Metal Bulletin was stable at \$55 per metric ton unit (\$50 per short ton unit) from January until mid-May, when it decreased to \$53 per metric ton unit (\$48 per short ton unit). Between late May and mid-October, the average price increased, and then remained at \$60 per metric ton unit (\$55 per short ton unit) until yearend. Ammonium paratungstate prices quoted by Platt's Metals Week and Metal Bulletin for the European and the Hong Kong markets followed similar trends.

The increase in tungsten prices during the second half of 1999 was attributed to efforts by China, the world's largest tungsten supplier, to reform its industry and to ensure a fair return to its domestic producers of concentrates and intermediate products (Maby, 1999, p. 8-9; Ross, 1999, p. 4). These efforts are discussed in more detail in the China section of this report.

In 1996, mine executives at the Seventh International Tungsten Symposium had stated that tungsten concentrate prices would need to increase to more than \$80 per metric ton unit and ammonium paratungstate prices would need to increase to more than \$100 per metric ton unit for it to be economical to bring back the more-than 10,000 t/yr of capacity lost during the previous 15 years (American Metal Market, 1996).

Foreign Trade

The United States exported 21% less tungsten in 1999 than in 1998. As shown in tables 6 through 10, exports of all tungsten materials except ores and concentrates, waste and scrap, and wrought tungsten were lower in 1999 compared with those of 1998.

In 1999, total U.S. imports of tungsten materials were 16% lower compared with those of 1998. China, which continued to be the largest supplier of tungsten to the United States, provided 45% of all tungsten imports in 1999. Imports from China decreased by 7% to 5,000 t of contained tungsten compared with 5,360 t imported in 1998. Of the imports from China, 35% was ammonium paratungstate; 30%, tungsten oxides; 15%, other tungstates; 10%, ferrotungsten; 3%, tungsten metal powders; 3%, tungsten waste and scrap; 2%, tungsten carbide powder; and the remainder, wrought tungsten.

Russia, which was the next largest supplier of tungsten materials to the United States, provided 21% of U.S. imports. In 1999, Russian imports were mainly tungsten ores and concentrates (52%), tungsten oxide (24%), tungsten waste and scrap (15%), and ferrotungsten (7%). Total imports from Russia decreased by 18% to 2,300 t of contained tungsten in 1999 compared with 2,790 t in 1998.

As shown in table 11, U.S. imports of tungsten ores and concentrates decreased by 39% in 1999 compared with those of 1998. In 1999, 83% of these imports were from Russia (42%), Kazakhstan (16%), Bolivia (13%), and Portugal (12%).

The United States imported approximately the same amount of ammonium paratungstate during the past 2 years (table 12). China continued to be the leading supplier of imported ammonium paratungstate to the United States, although imports of Chinese ammonium paratungstate to the United States decreased by 7% in 1999 compared with those of 1998. Imports of ammonium paratungstate from Germany, the Netherlands, and Sweden increased significantly in 1999 compared with those of 1998.

In 1999, imports of tungsten carbide powder, tungsten metal powders, and unwrought tungsten decreased compared with those of 1998, but imports of ferrotungsten, other tungstates, other tungsten compounds, and wrought tungsten increased. Imports of tungsten oxides and tungsten waste and scrap were at similar levels during the past 2 years (tables 13, 14).

World Review

In 1999, low tungsten prices resulted in a continued decrease in production of tungsten concentrates (table 15). Tungsten materials from stockpiles in Russia and other countries in the Commonwealth of Independent States (CIS) have been a significant component of world supply in recent years. Between 1992, when exports of tungsten from CIS countries first entered western markets, and mid-1999, an estimated 37,000 t of tungsten was exported. Information on the amount of tungsten that remained in CIS stockpiles and whether these

materials would be released for export continued to be unavailable, however (Maby, 1999, p. 2).

Austria.—Wolfram Bergbau und Hutten GmbH Nfg KG produced tungsten concentrates from the Mittersill scheelite mine in the Province of Salzburg. All these concentrates were converted to primary tungsten products at Wolfram Bergbau's Bergla tungsten processing plant in the Province of Steiermark.

China.—As part of the reformation and reorganization of China's nonferrous metals industry, the Chinese State Council approved the establishment of three corporations to operate as holding companies under supervision of the central government. All the mines, plants, and research institutes formerly under China National Nonferrous Metals Corp. were reorganized under China Aluminum Corp., China Copper Lead Zinc Corp., and China Rare Metals and Rare Earth Group Corp. China Rare Metals and Rare Earth Group Corp., which included tungsten mines and plants, was to be subdivided into several smaller groups. One of these subgroups, China Tungsten & Cemented Carbide Industry Corp., which consisted of Zhuzhou Cemented Carbide Works, Zigong Cemented Carbide Co., and Jinhai Industry Co., was established in February. Another subgroup, China Tungsten Mining & Smelting Group, was to include 10 State-owned tungsten mines in 3 provinces when established (Zhaoqing and Pugang, 1999).

In 1999, the Chinese Government took several steps to control the release of tungsten to the world market to increase prices to a level which would enable China's large State-owned producers to increase revenues without altering China's dominant position in the market. Early in the year, the Ministry of Land and Natural Resources ordered a halt to the operation of illegal mines and mines that were causing environmental damage or resource destruction and announced that it would not issue mining permits for new tungsten projects between April 23, 1999, and December 31, 2000. In June, following a meeting of Chinese Government agencies and several tungsten producers, the Government reduced the number of export licences for tungsten materials (American Metal Market, 1999; Kerr, 1999, p. 1-3; Metal Bulletin, 1999b).

In an effort to bring the prices of tungsten materials closer to the costs of production, the China Tungsten Industry Association set minimum prices for ammonium paratungstate, tungsten concentrates, and tungsten oxide in July. The prices were to be raised incrementally during a 3-year period (Metal Bulletin, 1999a).

Portugal.—During the fiscal year ending March 1999, Beralt Tin & Wolfram S.A., an Avocet subsidiary, reduced production from the Panasqueira Mine to match a decrease in sales. As a result, concentrate production decreased to 93,000 metric ton units (mtu) of WO_3 compared with the 131,700 mtu produced during the previous fiscal year. In April, the Portugese Government agreed to provide financial support in the form of a training subsidy that allowed Beralt to operate the mine 3 days per week without reducing its workforce. To return to full single shift production in January 2000, Beralt established sales contracts with two large tungsten consumers that guaranteed minimum sales volumes and prices (Avocet Mining PLC, September 29, 1999, Review of operations—Tungsten, Annual

Report and Accounts 1999, accessed June 26, 2000, at URL <http://www.avocet.co.uk/accounts/1999AR/operations.htm>).

Russia.—In October, the Russian Government recommended that the Government of the Republic of Kabardino-Balkaria consider investment projects at the Tyrnyauz tungsten and molybdenum mine and mill complex and the Gidrometallurg tungsten anhydride plant in Nalchik (Interfax International Ltd., 1999).

Thailand.—Scheelite was mined in Chiang Mai Province and wolframite was mined in Kanchaburi Province.

Outlook

Demand for tungsten tends to follow general economic conditions. Future consumption of tungsten in cemented carbides, which is the largest end-use sector, will depend on the performance of the following industries: automotive and aircraft production, construction, mining, oil and gas drilling, and semiconductor and other manufacturing. An increase in demand could help reduce the oversupply situation for tungsten. Some recent developments in uses for tungsten include the shift from lead to tungsten for military and recreational ammunition and the use of tungsten by the sporting goods industry to make golf clubs and golf ball cores. One analyst estimated that world tungsten demand would increase by 625 t, or approximately 1%, in 2000 for these and other new applications (Ross, 1999, p. 15).

World tungsten supply will continue to be dominated by Chinese production and exports. In 1999, the Chinese Government took several steps to control the release of tungsten to the market, which resulted in an increase in prices of tungsten concentrates and ammonium paratungstate during the second half of the year. Tungsten concentrate and ammonium paratungstate prices, however, leveled off by yearend. During the first half of 2000, prices for ammonium paratungstate decreased, and the price of tungsten concentrate increased slightly. This resulted in a narrowing of the price differential between concentrates and ammonium paratungstate, which would decrease the profitability of converting concentrates to ammonium paratungstate.

In 1999, a "new" source of supply became available to the tungsten market when the U.S. Government began selling tungsten materials from the NDS. Most of the tungsten in the stockpile is in the form of tungsten ores and concentrates. At yearend 1999, the NDS contained 33,300 t of tungsten in uncommitted ores and concentrates, all of which was authorized for eventual disposal. If future sales were to continue at the current AMP level (1,810 t in fiscal year 2000), then tungsten concentrates would be available from the NDS for many years to come. The amount of tungsten materials released from stockpiles has been an ongoing concern for the tungsten producing industry. In the middle to late 1990's, releases of stockpiled tungsten from Kazakhstan and Russia sustained the oversupply situation, kept prices low, and resulted in further hardship for the remaining tungsten mining industry. In recent years, approximately one-quarter of the world's tungsten supply has been from Government stockpile releases (Bunting, 1999). At some point, stockpiles will be depleted,

and world mine production will have to increase to meet demand. World mine capacity in 1998 was estimated to be less than world demand (Bunting, 1999). How quickly mines can be brought back online and whether mine production can meet demand once stockpiles are depleted will determine the future tungsten supply-demand balance.

References Cited

- American Metal Market, 1996, U.S. tungsten market expected to rebound: American Metal Market, v. 104, no. 192, October 3, p. 4.
- 1998, New Nanodyne plant to produce smallest tungsten grain: American Metal Market, v. 106, no. 165, August 27, p. 5.
- 1999, China halts new mining permits for 8 minerals: American Metal Market, v. 107, no. 103, May 28, p. 5.
- Bunting, R.M., 1999, Tungsten: Engineering and Mining Journal, v. 200, no. 3, March, p. 43-46.
- Defense National Stockpile Center, 2000, Revised FY 2000 Annual Materials Plan: Fort Belvoir, VA, Defense National Stockpile Center news release, April 3, 3 p.
- Interfax International Ltd., 1999, Russia to resuscitate tungsten-molybdenum industry: Mining & Metals Report, v. 8, issue 43 (397), October 15-21, p. 8.
- International Trade Administration, 1999a, August 1999 Sunset reviews—Termination of review, final results of reviews and revocation and termination: Federal Register, v. 64, no. 212, November 3, p. 59737-59738.
- 1999b, Initiation of five-year (“Sunset”) reviews: Federal Register, v. 64, no. 147, August 2, p. 41915-41916.
- Kerr, A.J., 1999, Ferro tungsten—2000 the new era: Ryan’s Notes Annual Ferroalloys Conference, Boca Raton, FL, October 24-26, 1999, Proceedings, 20 p.
- Maby, Michael, 1999, Market report by the Secretary-General, *in* Tungsten—Advanced technology & new applications: International Tungsten Symposium, 8th, Fukuoka, Japan, October 12-15, 1999, Transcripts of Papers, 15 p.
- Metal Bulletin, 1999a, China sets floor price for tungsten: Metal Bulletin, no. 8396, July 26, p. 8.
- 1999b, China shakes up tungsten industry: Metal Bulletin, no. 8383, June 10, p. 8.
- North American Tungsten Corp. Ltd., 1998, Tungsten ore shortages appear imminent: Vancouver, British Columbia, North American Tungsten Corp. Ltd. news release, November 13, 1 p.
- 1999, [Untitled]: Vancouver, British Columbia, North American Tungsten Corp. Ltd. news release, March 8, 1 p.
- N.V. Union Minière S.A., 2000, Annual report 1999: Brussels, N.V. Union Minière S.A., 52 p.
- Ross, B.M., 1999, U.S. tungsten market update, *in* Tungsten—Advanced technology & new applications: International Tungsten Symposium, 8th, Fukuoka, Japan, October 12-15, 1999, Transcripts of Papers, London, 15 p.
- U.S. Department of Defense, 2000, Strategic and critical materials report to the Congress—Operations under the Strategic and Critical Materials Stock Piling Act during the period October 1998 through September 1999: U.S. Department of Defense, 50 p.
- U.S. Fish and Wildlife Service, 1999, Migratory bird hunting—Final approval of tungsten-iron and tungsten-polymer shots and temporary approval of tungsten-matrix and tin shots as nontoxic for hunting waterfowl and coots—Final rule: Federal Register, v. 64, no. 160, August 19, p. 45400-45405.
- U.S. International Trade Commission, 1999a, Tungsten ore concentrates from China: Federal Register, v. 64, no. 147, August 2, p. 41963-41965.
- 1999b, Tungsten ore concentrates from China and uranium from

Kyrgyzstan: Federal Register, v. 64, no. 219, November 15, p. 61939.

Zhaoqing, Kong, and Pugang, Peng, 1999, The tungsten resources and developing prospect of the mining industry in China, *in* Tungsten—Advanced technology & new applications: International Tungsten Symposium, 8th, Fukuoka, Japan, October 12-15, 1999, Transcripts of Papers, London, 7 p.

GENERAL SOURCES OF INFORMATION

U.S. Geological Survey Publications

- Recycling—Metals. Ch. in Minerals Yearbook, annual.¹
- Tungsten. Ch. in Metal Prices in the United States through 1998, 1999.
- Tungsten. Ch. in Mineral Commodity Summaries, annual.¹
- Tungsten. Ch. in Minerals Yearbook, annual.¹
- Tungsten. Ch. in United States Mineral Resources, Professional Paper 820, 1973.
- Tungsten. International Strategic Mineral Issues Summary Report, Circular 930-O, 1998.
- Tungsten. Mineral Industry Surveys, monthly.¹

Other



- American Metal Market, daily.
- Company annual reports.
- Defense Logistics Agency, Defense National Stockpile Center.
- Engineering and Mining Journal, monthly.
- Federal Register, daily.
- Interfax International Ltd., Mining & Metals Report, weekly.
- International Tungsten Industry Association [United Kingdom].
- Materials flow of tungsten in the United States, U.S. Bureau of Mines Information Circular 9388, 1994.
- Metal Bulletin [London], semiweekly and monthly.
- Mining Journal [London], weekly, Metals & Minerals Annual Review, Mining Annual Review.
- Platt’s Metals Week, weekly.
- Roskill Information Services Ltd. [London].
- Ryan’s Notes, weekly.
- Strategic and Critical Materials Report to the Congress, Department of Defense.
- The tungsten industry of the U.S.S.R., U.S. Bureau of Mines Mineral Issues, 1988.
- Tungsten. Ch. in Mineral facts and problems. U.S. Bureau of Mines Bulletin 675, 1985.

¹Prior to January 1996, published by the U.S. Bureau of Mines.

TABLE 1
SALIENT TUNGSTEN STATISTICS 1/

(Metric tons tungsten content, unless otherwise specified)

| | 1995 | 1996 | 1997 | 1998 | 1999 |
|--|----------|-----------|----------|-----------|----------|
| United States: | | | | | |
| Concentrates: | | | | | |
| Consumption | 5,890 | 5,260 | 6,590 | 3,210 2/ | 2,100 2/ |
| Exports | 5 r/ | 18 r/ | 12 r/ | 10 r/ | 26 |
| Imports for consumption | 4,660 | 4,190 | 4,850 | 4,750 | 2,870 |
| Stocks, December 31: | | | | | |
| Consumer | 627 | 569 | 658 | 514 | W |
| U.S. Government 3/ | 34,600 | 34,600 | 34,600 | 34,600 | 34,600 |
| Ammonium paratungstate: | | | | | |
| Production | 2,580 4/ | 4,450 5/ | 5,380 5/ | 838 6/ | 7,330 |
| Consumption | 7,920 | 7,790 | 9,300 | 10,000 r/ | 7,490 |
| Stocks, December 31, producer and consumer | 727 | 558 | W | 603 | 376 |
| Primary products: | | | | | |
| Net production | 8,060 | 7,810 | 8,300 | 9,630 | 8,500 |
| Consumption 7/ | 8,800 | 7,830 | 8,390 | 9,100 | 8,390 |
| Stocks, December 31: | | | | | |
| Producer 8/ | 1,300 | 1,400 | 1,210 | 1,340 | 1,070 |
| Consumer 7/ | 564 r/ | 413 | 610 | 524 r/ | 565 |
| U.S. Government 3/ | 2,380 | 2,700 | 2,700 | 2,700 | 2,700 |
| World, production of concentrate | 38,500 | 34,800 r/ | 33,200 | 32,000 r/ | 31,000 |

r/ Revised. W Withheld to avoid disclosing company proprietary data.

1/ Data are rounded to no more than three significant digits.

2/ Excludes 6 months of "Withheld" data.

3/ Defense National Stockpile Center. Includes material committed for sale pending shipment.

4/ Excludes 7 months of "Withheld" data.

5/ Excludes 4 months of "Withheld" data.

6/ Excludes 11 months of "Withheld" data.

7/ Includes scrap.

8/ Excludes cast and crystalline tungsten carbide powder.

TABLE 2
U.S. GOVERNMENT NATIONAL DEFENSE STOCKPILE TUNGSTEN STATISTICS IN 1999 1/ 2/

(Metric tons tungsten content)

| Material | Inventory, yearend 3/ | | Annual Materials Plan | Sales | | Inventory decrease 4/ | |
|-------------------------|-----------------------|---------------|-----------------------|----------------|---------------|-----------------------|---------------|
| | Fiscal year 5/ | Calendar year | Fiscal year 5/ | Fiscal year 5/ | Calendar year | Fiscal year 5/ | Calendar year |
| Ores and concentrates | 34,600 | 34,600 | 1,360 | 1,350 | 1,350 | (6/) | (6/) |
| Ferrotungsten | 918 | 918 | 136 | 91 | 148 | -- | -- |
| Tungsten metal powder | 861 | 861 | 68 | 36 | 104 | (6/) | (6/) |
| Tungsten carbide powder | 922 | 922 | 454 | 111 | 284 | (6/) | (6/) |
| Total | 37,300 | 37,300 | 2,020 | 1,590 | 1,890 | (6/) | (6/) |

-- Zero.

1/ Data are rounded to no more than three significant digits; may not add to totals shown.

2/ Includes stockpile- and nonstockpile-grade materials.

3/ Includes material committed for sale pending shipment.

4/ From previous year.

5/ Twelve-month period ending September 30, 1999.

6/ Less than 1/2 unit.

Source: Defense National Stockpile Center.

TABLE 3
NET PRODUCTION AND STOCKS OF TUNGSTEN PRODUCTS IN THE UNITED STATES 1/ 2/

(Metric tons tungsten content)

| | Hydrogen reduced metal powder | Tungsten carbide powder | | Chemicals | Total |
|-------------------------|--|---------------------------|-------------------------|-----------|-------|
| | | Made from metal powder | Cast and crystalline | | |
| Net production: | | | | | |
| 1998 | 4,600 | 5,040 | W | W | 9,630 |
| 1999 | 4,540 | 3,960 | W | W | 8,500 |
| Producer stocks: | | | | | |
| December 31, 1998 | 719 | 576 | W | 46 | 1,340 |
| December 31, 1999 | 626 | 441 | W | W | 1,070 |

W Withheld to avoid disclosing company proprietary data.

1/ Net production equals gross production less quantity used to make other products in table.

2/ Data are rounded to no more than three significant digits; may not add to totals shown.

TABLE 4
REPORTED CONSUMPTION AND STOCKS OF TUNGSTEN PRODUCTS
IN THE UNITED STATES 1/ 2/ 3/

(Metric tons tungsten content)

| | 1998 | 1999 |
|--------------------------------------|---------------|--------------|
| Consumption by end use: | | |
| Steels | 532 | 486 |
| Superalloys | 333 | 306 |
| Other alloys 4/ | 219 | 189 |
| Cemented carbides 5/ | 6,640 | 5,910 |
| Mill products made from metal powder | 1,270 | 1,410 |
| Chemical uses | 97 | 93 |
| Total | 9,100 | 8,390 |
| Consumption by form: | | |
| Ferrotungsten | 527 | 484 |
| Tungsten metal powder | 1,370 | 1,500 |
| Tungsten carbide powder | 6,560 | 5,930 |
| Tungsten scrap | 516 | 356 |
| Other tungsten materials 6/ | 121 | 125 |
| Total | 9,100 | 8,390 |
| Consumer stocks, December 31: | | |
| Ferrotungsten | 26 | 33 |
| Tungsten metal powder | 17 | 15 |
| Tungsten carbide powder | 420 r/ | 475 |
| Tungsten scrap | 38 | 23 |
| Other tungsten materials 6/ | 24 | 19 |
| Total | 524 r/ | 565 |

r/ Revised.

1/ Data are rounded to no more than three significant digits; may not add to totals shown.

2/ Does not include materials used in making primary tungsten products.

3/ Includes estimates.

4/ Includes welding and hard-facing rods and materials, wear- and corrosion-resistant alloys, and nonferrous alloys.

5/ Includes diamond bit matrices, cemented and sintered carbides, and cast carbide dies or parts.

6/ Includes tungsten chemicals.

TABLE 5
MONTHLY PRICE QUOTATIONS OF TUNGSTEN CONCENTRATES IN 1999

| Month | Metal Bulletin (London), European market, 65% WO ₃ basis, c.i.f. 1/ | | | Platt's Metals Week, U.S. spot quotations, 65% WO ₃ basis, c.i.f. U.S. ports, including duty 2/ | | | | |
|-----------|---|------|---------|---|----------------------------|------|---------|--------------------------------|
| | Dollars per metric ton unit | | | Dollars per short ton unit | Dollars per short ton unit | | | Dollars per metric ton unit |
| | Low | High | Average | Average | Low | High | Average | Average |
| January | 32 | 44 | 38 | 34 | 40 | 45 | 43 | 47 |
| February | 33 | 44 | 39 | 35 | 40 | 45 | 43 | 47 |
| March | 33 | 44 | 39 | 35 | 40 | 45 | 43 | 47 |
| April | 33 | 44 | 39 | 35 | 40 | 45 | 43 | 47 |
| May | 33 | 44 | 39 | 35 | 40 | 45 | 43 | 47 |
| June | 33 | 44 | 39 | 35 | 40 | 45 | 43 | 47 |
| July | 33 | 44 | 39 | 35 | 40 | 45 | 43 | 47 |
| August | 33 | 48 | 41 | 37 | 40 | 45 | 43 | 47 |
| September | 38 | 48 | 43 | 39 | 40 | 45 | 43 | 47 |
| October | 38 | 48 | 43 | 39 | 40 | 45 | 43 | 47 |
| November | 38 | 48 | 43 | 39 | 40 | 45 | 43 | 47 |
| December | 38 | 48 | 43 | 39 | 40 | 45 | 43 | 47 |

1/ Combined wolframite and scheelite quotations. Low and high prices are reported semiweekly. Monthly averages are arithmetic averages of semiweekly low and high prices. The average annual price per metric ton unit of WO₃ of all semiweekly low and high prices was \$40 in 1999. The average equivalent price per short ton unit of WO₃ was \$36 in 1999.

2/ Low and high prices are reported weekly. Monthly averages are arithmetic averages of weekly low and high prices. The average annual price per short ton unit of WO₃ of all weekly low and high prices was \$43 in 1999. The average equivalent price per metric ton unit of WO₃ was \$47 in 1999.

TABLE 6
U.S. EXPORTS OF TUNGSTEN ORES AND CONCENTRATES, BY COUNTRY

| Country of destination | 1998 | | | 1999 | | |
|------------------------|-------------------------------|---|----------------------|-------------------------------|---|----------------------|
| | Gross weight (metric tons) | Tungsten content 1/ (metric tons) | Value (thousands) | Gross weight (metric tons) | Tungsten content 1/ (metric tons) | Value (thousands) |
| Afghanistan | -- | -- | -- | (2/) | (2/) | \$4 |
| Belgium | (2/) | (3/) | \$6 | -- | -- | -- |
| Brazil | (2/) | (3/) | 4 | 1 | (2/) | 9 |
| Colombia | (2/) | (3/) | 5 | -- | -- | -- |
| Ecuador | -- | -- | -- | 1 | (2/) | 11 |
| Germany | 2 | 1 r/ | 36 | 2 | 1 | 23 |
| Ireland | 6 | 3 r/ | 89 | 5 | 3 | 83 |
| Italy | 2 | 1 r/ | 37 | -- | -- | -- |
| Japan | (2/) | (2/) | 3 | 1 | (2/) | 17 |
| Korea, Republic of | -- | -- | -- | 1 | 1 | 20 |
| Mexico | (2/) | (2/) | 3 | (2/) | (2/) | 4 |
| Netherlands | -- | -- | -- | 27 | 14 | 462 |
| Singapore | -- | -- | -- | (2/) | (2/) | 6 |
| Thailand | -- | -- | -- | 1 | 1 | 21 |
| United Kingdom | 8 | 4 r/ | 117 | 11 | 6 | 166 |
| Total 4/ | 19 | 10 r/ | 300 | 51 | 26 | 826 |

r/ Revised. -- Zero.

1/ Content estimated from reported gross weight.

2/ Less than 1/2 unit.

3/ Revised to less than 1/2 unit.

4/ Data may not add to totals shown because of independent rounding.

Source: U.S. Census Bureau.

TABLE 7
U.S. EXPORTS OF AMMONIUM PARATUNGSTATE, BY COUNTRY 1/

| Country of destination | 1998 | | 1999 | |
|------------------------|--------------------------------|-------------------|--------------------------------|-------------------|
| | Tungsten content (metric tons) | Value (thousands) | Tungsten content (metric tons) | Value (thousands) |
| Belgium | 72 | \$744 | 79 | \$673 |
| Denmark | -- | -- | 7 | 71 |
| France | 1 | 8 | -- | -- |
| Germany | 37 | 194 | 9 | 80 |
| Hungary | 1 | 9 | -- | -- |
| Japan | -- | -- | 6 | 56 |
| Korea, Republic of | -- | -- | (2/) | 4 |
| Mexico | -- | -- | (2/) | 23 |
| Spain | -- | -- | (2/) | 4 |
| Sweden | 95 | 708 | -- | -- |
| United Kingdom | 82 | 535 | -- | -- |
| Total | 287 | 2,200 | 103 | 911 |

-- Zero.

1/ Data are rounded to no more than three significant digits; may not add to totals shown.

2/ Less than 1/2 unit.

Source: U.S. Census Bureau.

TABLE 8
U.S. EXPORTS OF TUNGSTEN METAL POWDERS, BY COUNTRY 1/ 2/

| Country of destination | 1998 | | | 1999 | | |
|------------------------|----------------------------|-----------------------------------|-------------------|----------------------------|-----------------------------------|-------------------|
| | Gross weight (metric tons) | Tungsten content 3/ (metric tons) | Value (thousands) | Gross weight (metric tons) | Tungsten content 3/ (metric tons) | Value (thousands) |
| Australia | 5 | 4 | \$139 | 12 | 9 | \$163 |
| Austria | (4/) | (4/) | 6 | 2 | 2 | 50 |
| Belgium | 12 | 10 | 124 | 45 | 36 | 392 |
| Brazil | 17 | 14 | 415 | 7 | 6 | 212 |
| Canada | 59 | 47 | 1,930 | 57 | 46 | 1,500 |
| Chile | (4/) | (4/) | 12 | 4 | 3 | 161 |
| China | 5 | 4 | 114 | (4/) | (4/) | 19 |
| Congo (Kinshasa) | -- | -- | -- | 10 | 8 | 51 |
| France | 15 | 12 | 513 | 31 | 25 | 673 |
| Germany | 408 | 326 | 12,900 | 236 | 188 | 6,570 |
| Hong Kong | 3 | 2 | 84 | 19 | 15 | 29 |
| India | 83 | 66 | 1,160 | 90 | 72 | 1,570 |
| Israel | 38 | 30 | 466 | 41 | 33 | 494 |
| Italy | 14 | 12 | 700 | 21 | 17 | 813 |
| Japan | 75 | 60 | 565 | 48 | 38 | 624 |
| Korea, Republic of | 5 | 4 | 197 | 8 | 6 | 132 |
| Mexico | 9 | 7 | 224 | 34 | 27 | 338 |
| Netherlands | 19 | 15 | 421 | 25 | 20 | 733 |
| Panama | 11 | 9 | 13 | 2 | 1 | 33 |
| Poland | -- | -- | -- | 3 | 2 | 100 |
| Singapore | 4 | 3 | 273 | 6 | 5 | 325 |
| South Africa | 3 | 2 | 111 | 4 | 3 | 61 |
| Spain | 1 | 1 | 40 | 1 | 1 | 60 |
| Sweden | 3 | 2 | 50 | 76 | 61 | 395 |
| Switzerland | 59 | 48 | 2,420 | 30 | 24 | 947 |
| Taiwan | 16 | 13 | 482 | 22 | 17 | 587 |
| United Kingdom | 193 | 154 | 2,140 | 51 | 41 | 1,810 |
| Other | 7 | 6 r/ | 207 r/ | 5 | 4 | 157 |
| Total | 1,060 | 851 | 25,700 | 889 | 711 | 19,000 |

r/ Revised. -- Zero.

1/ Data are rounded to no more than three significant digits; may not add to totals shown.

2/ May include tungsten alloy powders.

3/ Content estimated from reported gross weight.

4/ Less than 1/2 unit.

Source: U.S. Census Bureau.

TABLE 9
U.S. EXPORTS OF TUNGSTEN CARBIDE POWDER, BY COUNTRY 1/

| Country of destination | 1998 | | 1999 | |
|------------------------|--------------------------------|-------------------|--------------------------------|-------------------|
| | Tungsten content (metric tons) | Value (thousands) | Tungsten content (metric tons) | Value (thousands) |
| Argentina | 1 | \$46 | 2 | \$12 |
| Australia | 7 | 157 | 7 | 182 |
| Austria | 22 | 463 | 20 | 362 |
| Belgium | 8 | 291 | 20 | 413 |
| Brazil | 7 | 264 | 6 | 195 |
| Canada | 224 | 5,680 | 177 | 4,490 |
| Czech Republic | -- | -- | 5 | 65 |
| France | 10 | 234 | 25 | 241 |
| Germany | 272 | 4,620 | 163 | 4,800 |
| Hong Kong | (2/) | 3 | 11 | 165 |
| India | 2 | 72 | 5 | 107 |
| Ireland | 2 | 170 | 8 | 282 |
| Israel | 106 | 1,370 | 26 | 313 |
| Italy | 96 | 2,490 | 62 | 1,630 |
| Japan | 28 | 1,040 | 15 | 808 |
| Korea, Republic of | 6 | 256 | 6 | 228 |
| Luxembourg | 2 | 38 | 13 | 158 |
| Malaysia | 1 | 40 | (2/) | 22 |
| Mexico | 13 | 491 | 3 | 61 |
| Netherlands | 240 | 3,780 | 53 | 736 |
| Portugal | 17 | 254 | -- | -- |
| Singapore | 4 | 272 | 1 | 91 |
| South Africa | 35 | 459 | 21 | 314 |
| Spain | 1 | 49 | (2/) | 10 |
| Sweden | 25 | 338 | 20 | 287 |
| Switzerland | 3 | 126 | 2 | 122 |
| Taiwan | 15 | 455 | (2/) | 19 |
| United Arab Emirates | 1 | 22 | -- | -- |
| United Kingdom | 80 | 1,310 | 27 | 622 |
| Venezuela | 13 | 292 | 1 | 53 |
| Other | 2 r/ | 68 r/ | 2 | 71 |
| Total | 1,240 | 25,200 | 701 | 16,900 |

r/ Revised. -- Zero.

1/ Data are rounded to no more than three significant digits; may not add to totals shown.

2/ Less than 1/2 unit.

Source: U.S. Census Bureau.

TABLE 10
U.S. EXPORTS OF MISCELLANEOUS TUNGSTEN-BEARING MATERIALS, BY COUNTRY 1/

| Product and country of destination | 1998 | | 1999 | |
|---|--------------------------------|-------------------|--------------------------------|-------------------|
| | Tungsten content (metric tons) | Value (thousands) | Tungsten content (metric tons) | Value (thousands) |
| Ferrotungsten and ferrosilicon tungsten: | | | | |
| Canada | 4 | \$62 | 2 | \$26 |
| Israel | (2/) | 4 | -- | -- |
| Korea, Republic of | 9 | 394 | -- | -- |
| Mexico | 14 | 407 | 2 | 20 |
| Netherlands | 5 | 222 | -- | -- |
| Venezuela | 9 | 367 | -- | -- |
| Total | 40 | 1,460 | 4 | 46 |
| Unwrought tungsten and waste and scrap: 3/ 4/ 5/ | | | | |
| Australia | 6 | 33 | 22 | 143 |
| Belgium | 1 | 14 | 76 | 436 |
| Brazil | (2/) | 12 | 1 | 11 |
| Canada | 49 | 422 | 5 | 77 |
| China | 2 | 11 | 2 | 7 |
| Colombia | 2 | 13 | -- | -- |
| Denmark | 12 | 68 | -- | -- |
| France | 31 | 177 | 1 | 10 |
| Germany | 319 | 1,650 | 226 | 1,230 |
| Hong Kong | 1 | 12 | 6 | 35 |
| Hungary | 3 | 15 | -- | -- |
| India | 10 | 169 | 72 | 1,160 |
| Ireland | 3 | 17 | (2/) | 9 |
| Israel | 19 | 106 | 29 | 151 |
| Italy | 18 | 82 | 20 | 122 |
| Japan | 39 | 222 | 24 | 136 |
| Korea, Republic of | 4 | 25 | 12 | 71 |
| Malaysia | 10 | 75 | 9 | 60 |
| Mexico | 27 | 169 | 42 | 252 |
| Netherlands | 22 | 159 | 27 | 168 |
| Norway | 3 | 18 | -- | -- |
| Philippines | 13 | 74 | 14 | 80 |
| Portugal | -- | -- | 4 | 23 |
| Singapore | 3 | 34 | 1 | 6 |
| Sweden | 19 | 160 | 4 | 23 |
| Taiwan | 95 | 757 | 58 | 464 |
| United Kingdom | 82 | 475 | 186 | 1,140 |
| Other | -- r/ | -- r/ | 2 | 15 |
| Total | 794 | 4,970 | 843 | 5,820 |
| Wrought tungsten--wire: 3/ 4/ | | | | |
| Belgium | 10 | 653 | 1 | 131 |
| Brazil | 10 | 741 | 11 | 695 |
| Canada | 21 | 749 | 10 | 458 |
| China | 1 | 117 | 3 | 290 |
| France | 8 | 576 | 9 | 924 |
| Germany | 3 | 480 | 1 | 179 |
| Hong Kong | 1 | 64 | 5 | 72 |
| Hungary | 5 | 223 | 16 | 868 |
| India | 19 | 1,360 | 22 | 1,400 |
| Indonesia | 3 | 207 | 2 | 117 |
| Italy | 6 | 366 | 2 | 249 |
| Japan | 7 | 897 | 14 | 935 |
| Mexico | 17 | 1,250 | 9 | 888 |
| Netherlands | (2/) | 59 | 3 | 105 |
| Spain | 3 | 130 | 6 | 386 |
| Sweden | 3 | 249 | 2 | 201 |
| Taiwan | 4 | 232 | (2/) | 38 |
| United Kingdom | 2 | 340 | 3 | 1,160 |
| Other | 2 r/ | 450 r/ | 4 | 549 |
| Total | 125 | 9,140 | 122 | 9,650 |

See footnotes at end of table.

TABLE 10--Continued
U.S. EXPORTS OF MISCELLANEOUS TUNGSTEN-BEARING MATERIALS, BY COUNTRY 1/

| Product and country of destination | 1998 | | 1999 | |
|--|--------------------------------|-------------------|--------------------------------|-------------------|
| | Tungsten content (metric tons) | Value (thousands) | Tungsten content (metric tons) | Value (thousands) |
| Wrought tungsten, excluding wire: 3/ 4/ | | | | |
| Argentina | 1 | \$27 | -- | -- |
| Brazil | 5 | 246 | 17 | 483 |
| Canada | 22 | 822 | 19 | 810 |
| Chile | 1 | 47 | (2/) | 5 |
| China | 1 | 162 | (2/) | 104 |
| France | 2 | 203 | 1 | 145 |
| Germany | 112 | 2,780 | 205 | 4,400 |
| India | 28 | 590 | 22 | 505 |
| Ireland | 1 | 24 | -- | -- |
| Israel | (2/) | 173 | 1 | 134 |
| Italy | 1 | 122 | 1 | 84 |
| Japan | 12 | 1,360 | 14 | 1,290 |
| Malaysia | (2/) | 3 | 1 | 25 |
| Mexico | 5 | 299 | 4 | 295 |
| Netherlands | 1 | 53 | 1 | 23 |
| Poland | -- | -- | 1 | 28 |
| Singapore | 1 | 108 | (2/) | 108 |
| Sweden | 1 | 128 | (2/) | 43 |
| Spain | 4 | 151 | -- | -- |
| Taiwan | 7 | 453 | 1 | 119 |
| United Kingdom | 2 | 213 | 6 | 376 |
| Venezuela | (2/) | 33 | 1 | 21 |
| Other | 1 | 181 r/ | 2 | 213 |
| Total | 207 | 8,180 | 297 | 9,210 |
| Other tungsten metal: 3/ 4/ | | | | |
| Australia | 1 | 147 | 6 | 527 |
| Brazil | 1 | 111 | 1 | 130 |
| Canada | 12 | 760 | 10 | 634 |
| Finland | -- | -- | 1 | 95 |
| France | 1 | 75 | 1 | 162 |
| Germany | 3 | 706 | 2 | 520 |
| Hong Kong | 4 | 174 | (2/) | 53 |
| India | 2 | 137 | 1 | 52 |
| Israel | 7 | 1,170 | 5 | 1,100 |
| Japan | 5 | 2,280 | 5 | 1,940 |
| Korea, Republic of | 4 | 285 | 2 | 167 |
| Mexico | 5 | 707 | 8 | 846 |
| Netherlands | 2 | 288 | 1 | 88 |
| Singapore | 1 | 362 | 1 | 431 |
| Taiwan | 8 | 714 | 3 | 487 |
| Turkey | (2/) | 17 | 1 | 34 |
| United Kingdom | 6 | 495 | 7 | 977 |
| Other | 4 | 739 r/ | 3 | 637 |
| Total | 64 | 9,170 | 57 | 8,880 |
| Tungsten compounds: 6/ | | | | |
| Belgium | -- | -- | 16 | 291 |
| Canada | 11 | 28 | 1 | 3 |
| El Salvador | 19 | 27 | -- | -- |
| Mexico | (2/) | 7 | -- | -- |
| United Kingdom | -- | -- | 1 | 23 |
| Total | 31 | 62 | 18 | 317 |

r/ Revised. -- Zero.

1/ Data are rounded to no more than three significant digits; may not add to totals shown.

2/ Less than 1/2 unit.

3/ May include alloys.

4/ Content estimated from reported gross weight.

5/ Includes bars and rods obtained by sintering.

6/ Includes only other tungstates.

Source: U.S. Census Bureau.

TABLE 11
U.S. IMPORTS FOR CONSUMPTION OF TUNGSTEN ORES AND CONCENTRATES, BY COUNTRY 1/

| Country of origin | 1998 | | 1999 | |
|-------------------|--------------------------------|-------------------|--------------------------------|-------------------|
| | Tungsten content (metric tons) | Value (thousands) | Tungsten content (metric tons) | Value (thousands) |
| Australia | 72 | \$308 | 167 | \$601 |
| Bolivia | 619 | 3,000 | 361 | 1,670 |
| Burma | -- | -- | 91 | 283 |
| Chile | 12 | 57 | -- | -- |
| Germany | 52 | 238 | -- | -- |
| Japan | 10 | 54 | -- | -- |
| Kazakhstan | 782 | 3,570 | 461 | 1,610 |
| Mexico | 132 | 490 | 27 | 75 |
| Mongolia | 24 | 74 | 55 | 138 |
| Netherlands | 33 | 152 | -- | -- |
| Peru | 85 | 451 | 22 | 136 |
| Portugal | 643 | 3,770 | 353 | 1,960 |
| Russia | 2,140 | 9,070 | 1,200 | 5,440 |
| Rwanda | 82 | 302 | 55 | 154 |
| Thailand | 12 | 70 | 11 | 45 |
| United Kingdom | 49 | 270 | 72 | 274 |
| Total | 4,750 | 21,900 | 2,870 | 12,400 |

-- Zero.

1/ Data are rounded to no more than three significant digits; may not add to totals shown.

Source: U.S. Census Bureau.

TABLE 12
U.S. IMPORTS FOR CONSUMPTION OF AMMONIUM PARATUNGSTATE, BY COUNTRY 1/

| Country of origin | 1998 | | 1999 | |
|-------------------|--------------------------------|-------------------|--------------------------------|-------------------|
| | Tungsten content (metric tons) | Value (thousands) | Tungsten content (metric tons) | Value (thousands) |
| China | 1,900 | \$10,900 | 1,760 | \$9,070 |
| Germany | 3 | 137 | 103 | 968 |
| Japan | (2/) | 1 | -- | -- |
| Netherlands | -- | -- | 17 | 77 |
| Sweden | 18 | 91 | 34 | 115 |
| Total | 1,920 | 11,100 | 1,920 | 10,200 |

-- Zero.

1/ Data are rounded to no more than three significant digits; may not add to totals shown.

2/ Less than 1/2 unit.

Source: U.S. Census Bureau.

TABLE 13
U.S. IMPORTS FOR CONSUMPTION OF FERROTUNGSTEN AND FERROSILICON TUNGSTEN, BY COUNTRY 1/

| Country of origin | 1998 | | 1999 | |
|-------------------|--------------------------------|-------------------|--------------------------------|-------------------|
| | Tungsten content (metric tons) | Value (thousands) | Tungsten content (metric tons) | Value (thousands) |
| China | 261 | \$1,770 | 498 | \$2,930 |
| Germany | 1 | 13 | 3 | 38 |
| Russia | 324 | 2,000 | 168 | 793 |
| United Kingdom | 14 | 100 | -- | -- |
| Total | 599 | 3,890 | 669 | 3,760 |

-- Zero.

1/ Data are rounded to no more than three significant digits; may not add to totals shown.

Source: U.S. Census Bureau.

TABLE 14
U.S. IMPORTS FOR CONSUMPTION OF MISCELLANEOUS TUNGSTEN-BEARING MATERIALS, BY COUNTRY 1/

| Product and country of origin | 1998 | | 1999 | |
|-------------------------------------|-----------------------------------|----------------------|-----------------------------------|----------------------|
| | Tungsten content (metric tons) | Value (thousands) | Tungsten content (metric tons) | Value (thousands) |
| Tungsten metal powders: 2/ | | | | |
| Belgium | 4 | \$132 | 3 | \$122 |
| Canada | 6 | 164 | 4 | 117 |
| China | 122 | 1,850 | 145 | 2,000 |
| Czech Republic | 17 | 277 | -- | -- |
| France | 10 | 95 | -- | -- |
| Germany | 79 | 1,780 | 32 | 865 |
| Israel | 20 | 201 | 7 | 125 |
| Japan | 24 | 1,760 | 15 | 1,400 |
| Netherlands | 17 | 277 | -- | -- |
| Russia | -- | -- | 3 | 24 |
| United Kingdom | 145 | 1,330 | 100 | 927 |
| South Africa | 15 | 79 | (3/) | 2 |
| Other | (3/) | 8 | (3/) | 8 |
| Total | 459 | 7,950 | 310 | 5,590 |
| Tungsten carbide powder: | | | | |
| Austria | 62 | 1,030 | 43 | 639 |
| Canada | 432 | 7,510 | 412 | 6,590 |
| China | 286 | 4,410 | 113 | 1,740 |
| France | 2 | 84 | (3/) | 23 |
| Germany | 43 | 1,150 | 79 | 1,680 |
| Hong Kong | 3 | 49 | -- | -- |
| India | 16 | 245 | -- | -- |
| Israel | 84 | 1,420 | 77 | 1,700 |
| Japan | (3/) | 33 | 2 | 77 |
| Korea, Republic of | 4 | 77 | 10 | 44 |
| Luxembourg | 8 | 122 | 34 | 577 |
| Russia | 1 | 10 | 20 | 78 |
| United Kingdom | 2 | 41 | (3/) | 7 |
| Other | 1 r/ | 109 r/ | 1 | 93 |
| Total | 944 | 16,300 | 790 | 13,200 |
| Unwrought tungsten: 2/ 4/ 5/ | | | | |
| Austria | 4 | 319 | 2 | 170 |
| Canada | 3 | 35 | 3 | 11 |
| Germany | 4 | 190 | 2 | 234 |
| Russia | 10 | 111 | -- | -- |
| United Kingdom | 4 | 67 | (3/) | 12 |
| Other | (3/) | 9 | (3/) | 20 |
| Total | 24 | 730 | 8 | 447 |
| Waste and scrap: | | | | |
| Austria | 15 | 148 | 17 | 147 |
| Bermuda | 12 | 59 | 12 | 65 |
| Canada | 23 | 167 | 19 | 102 |
| China | 98 | 887 | 169 | 1,380 |
| Estonia | 11 | 69 | -- | -- |
| France | 21 | 154 | -- | -- |
| Germany | 241 | 1,810 | 151 | 779 |
| Hong Kong | 9 | 83 | 13 | 120 |
| India | 48 | 272 | 16 | 64 |
| Indonesia | 1 | 4 | 13 | 101 |
| Ireland | -- | -- | 13 | 114 |
| Israel | 74 | 370 | 21 | 71 |
| Japan | 240 | 1,670 | 314 | 1,530 |
| Korea, Republic of | 15 | 112 | 60 | 212 |
| Mexico | 9 | 44 | -- | -- |
| Netherlands | 53 | 395 | 13 | 110 |
| Russia | 280 | 1,500 | 343 | 1,810 |
| Singapore | 33 | 168 | 11 | 59 |
| South Africa | 69 | 543 | 72 | 462 |
| Sweden | -- | -- | 11 | 66 |

See footnotes at end of table.

TABLE 14--Continued
U.S. IMPORTS FOR CONSUMPTION OF MISCELLANEOUS TUNGSTEN-BEARING MATERIALS, BY COUNTRY 1/

| Product and country of origin | 1998 | | 1999 | |
|---|-----------------------------------|----------------------|-----------------------------------|----------------------|
| | Tungsten content (metric tons) | Value (thousands) | Tungsten content (metric tons) | Value (thousands) |
| Waste and scrap--Continued: | | | | |
| Taiwan | 2 | \$25 | -- | -- |
| Ukraine | -- | -- | 16 | \$154 |
| United Kingdom | 155 | 1,080 | 93 | 545 |
| Uzbekistan | 36 | 361 | 59 | 437 |
| Other | 11 r/ | 77 r/ | 2 | 12 |
| Total | 1,450 | 10,000 | 1,440 | 8,340 |
| Wrought tungsten wire, plate, sheet, strip, foil, other: 2/ 4/ | | | | |
| Austria | 16 | 3,260 | 17 | 2,490 |
| Canada | 2 | 62 | 21 | 649 |
| China | 31 | 1,360 | 24 | 1,330 |
| France | 4 | 234 | 2 | 302 |
| Germany | 26 | 3,410 | 78 | 6,270 |
| Hungary | 6 | 558 | 11 | 809 |
| India | 12 | 138 | (3/) | 30 |
| Israel | 28 | 2,060 | 11 | 1,010 |
| Japan | 30 | 5,950 | 28 | 5,600 |
| Mexico | 3 | 840 | 1 | 601 |
| Netherlands | (3/) | 184 | 1 | 245 |
| Russia | 25 | 191 | 15 | 121 |
| Switzerland | 16 | 1,450 | 3 | 416 |
| United Kingdom | 3 | 392 | 3 | 518 |
| Other | 5 | 303 | 2 | 239 |
| Total | 206 | 20,400 | 217 | 20,600 |
| Tungsten oxides: | | | | |
| China | 1,940 | 12,600 | 1,530 | 7,940 |
| Germany | 3 | 63 | 1 | 28 |
| Japan | 39 | 298 | -- | -- |
| Netherlands | (3/) | 4 | 19 | 102 |
| Russia | 14 | 69 | 555 | 2,350 |
| United Kingdom | 140 | 866 | 4 | 29 |
| Other | 1 | 11 r/ | (3/) | 5 |
| Total | 2,130 | 13,900 | 2,110 | 10,500 |
| Calcium tungstate, Japan | 1 | 127 | 1 | 24 |
| Other tungstates: | | | | |
| China | 723 | 3,290 | 763 | 3,240 |
| Germany | 2 | 75 | 8 | 143 |
| India | (3/) | 6 | -- | -- |
| Japan | (3/) | 2 | -- | -- |
| Mongolia | 11 | 45 | -- | -- |
| Total | 736 | 3,420 | 770 | 3,380 |
| Other tungsten compounds: 6/ | | | | |
| China | (3/) | 10 | -- | -- |
| France | -- | -- | (3/) | 3 |
| Germany | 1 | 81 | 1 | 143 |
| Japan | 1 | 257 | 2 | 513 |
| Total | 2 | 348 | 3 | 659 |

r/ Revised. -- Zero.

1/ Data are rounded to no more than three significant digits; may not add to totals shown.

2/ May include alloys.

3/ Less than 1/2 unit.

4/ Content estimated from reported gross weight.

5/ Includes bars and rods obtained by sintering; excludes powders, waste and scrap.

6/ Includes tungsten chlorides.

Source: U.S. Census Bureau.

TABLE 15
TUNGSTEN: WORLD CONCENTRATE PRODUCTION, BY COUNTRY 1/ 2/

(Metric tons, tungsten content)

| Country | 1995 | 1996 | 1997 | 1998 | 1999 |
|-----------------|--------|-----------|----------|-----------|--------|
| Austria | 738 | 1,413 | 1,400 e/ | 1,423 r/ | 1,610 |
| Bolivia | 655 | 582 | 513 | 497 | 334 |
| Brazil | 98 | 99 r/ | 40 r/ | -- r/ | -- |
| Burma 3/ | 531 | 334 | 272 | 178 r/ | 87 |
| Burundi e/ | 22 | 16 | 16 | 10 | 10 |
| China e/ 4/ | 27,400 | 26,500 | 25,000 | 24,700 | 24,000 |
| India | 4 | 2 | 1 r/ | -- r/ | -- |
| Kazakhstan | 249 | -- | -- | -- | -- |
| Korea, North e/ | 900 | 900 | 900 | 800 r/ | 700 |
| Mexico | 287 | 188 | 179 | 130 | 43 |
| Mongolia e/ | 34 | 17 | 26 | 35 r/ | 16 |
| Peru | 728 | 332 | 280 r/ | 76 | -- |
| Portugal | 875 | 776 | 1,036 | 831 e/ | 450 e/ |
| Russia e/ | 5,400 | 3,000 | 3,000 | 3,000 | 3,500 |
| Rwanda | 47 | 104 r/ | 78 r/ | 80 r/ e/ | 60 e/ |
| Tajikistan e/ | 75 | 50 | -- | -- | -- |
| Thailand e/ | 52 r/ | 37 r/ | 30 r/ | 35 r/ | 29 |
| Uganda | 17 | -- | -- | -- | -- |
| Uzbekistan e/ | 300 | 300 | 250 | 200 | 200 |
| Vietnam | 50 | 130 | 210 | -- r/ | -- |
| Total | 38,500 | 34,800 r/ | 33,200 | 32,000 r/ | 31,000 |

e/ Estimated. r/ Revised. -- Zero.

1/ World totals and estimated data are rounded to no more than three significant digits; may not add to totals shown.

2/ Tungsten concentrates are believed to be produced in Kyrgyzstan, but information is inadequate for making production estimates. Table includes data available through June 2, 2000.

3/ Includes content of tin-tungsten concentrate.

4/ Based upon data published in the Yearbook of Nonferrous Industry of China.

Collected By 
Chinatungsten Online